


MAIN AREA WATERPROOFING




TRIFLEX PROTECT® @ 3.00 Kg/m² MIN
WITH POWDER THIXO (2% MAX)
OR LIQUID THIXO (1% MAX)

TRIFLEX 110g REINFORCEMENT FLEECE

TRIFLEX PRIMER (IF REQUIRED - REFER TO
PROJECT SPECIFICATION PROPOSAL)

GENERIC SUBSTRATE (PREPARED)

* Where the roof becomes pitched there is a risk Triflex ProTect will slump. To compensate add Triflex Powder Thixo up to a maximum of 2% by weight or add Triflex Liquid Thixo up to 1% to increase the viscosity of the resin. Ensure Thixo agent is added prior to the application of catalyst, and thoroughly mixed. Triflex Liquid Thixo must be left for 20min prior to catalysing and application.




GENERAL NOTES

This drawing and any reference to structural / thermal elements should be treated as indicative only and read in conjunction with the Triflex Project specification proposal and relevant Triflex technical data. Details should be verified for accuracy and suitability as we specifically exclude any liability for errors, omissions or otherwise.

The drawing should not be reproduced or amended except with the written permission of Triflex. Do not scale, use figured dimensions only, and check all dimensions on site.

INDICATIVE SYSTEM BUILD-UP



SYSTEM

TRIFLEX PROTECT®

PROJECT

STANDARD

DETAIL

ROOF PITCH GREATER THAN
10 DEGREES

DRAWING NUMBER

PROTECT_024_ROOF PITCH
GREATER THAN 10 DEGREES

SCALE	DATE	REVISION
NTS	19/03/2019	-

Triflex
Delivering solutions together

Triflex (UK) Limited

Whitebridge Way | Stone | Staffs
ST15 8JS | Tel: 01785 819119
www.triflex.co.uk | info@triflex.co.uk



ROOFS | ROOF DETAILS | REPAIRS